

This Page Is Inserted by IFW Operations
and is not a part of the Official Record

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images may include (but are not limited to):


- BLACK BORDERS
- TEXT CUT OFF AT TOP, BOTTOM OR SIDES
- FADED TEXT
- ILLEGIBLE TEXT
- SKEWED/SLANTED IMAGES
- COLORED PHOTOS
- BLACK OR VERY BLACK AND WHITE DARK PHOTOS
- GRAY SCALE DOCUMENTS

IMAGES ARE BEST AVAILABLE COPY.

**As rescanning documents *will not* correct images,
please do not report the images to the
Image Problem Mailbox.**

Claims

508A, >
1. A non-aqueous electrolyte secondary battery comprising a negative electrode, a positive electrode and an electrolyte having a lithium salt dissolved in a non-aqueous solvent, characterized in that said non-aqueous solvent contains a vinyl ethylene carbonate compound represented by the following general formula (I) in an amount of from 0.01% to 20% by weight:



wherein R^1 , R^2 , R^3 , R^4 , R^5 and R^6 each independently represent a hydrogen atom or an alkyl group having 1 to 4 carbon atoms.

2. The non-aqueous electrolyte secondary battery according to Claim 1, wherein said negative electrode contains a carbon-based material capable of absorbing and releasing lithium.

3. The non-aqueous electrolyte secondary battery according to Claim 2, wherein said carbon-based material capable of absorbing and releasing lithium comprises a carbon-based material having a d value of from 0.335 to 0.34 nm on lattice

plane (002 plane) as determined by X-ray diffractometry.

508A₂ >
4. The non-aqueous electrolyte secondary battery according to any one of Claims 1 to 3, wherein said non-aqueous solvent is a mixed solvent containing a cyclic carbonate selected from the group consisting of alkylene carbonates the alkylene group moiety of which each have from 2 to 4 carbon atoms and a chain carbonate selected from the group consisting of dialkyl carbonate the alkyl group moiety of which each have from 1 to 4 carbon atoms except the vinyl ethylene carbonate compound of the general formula (I) each in an amount of not smaller than 20 vol-%, with the proviso that the content of said carbonates accounts for not smaller than 70 vol-% based on the total amount thereof.

5. The non-aqueous electrolyte secondary battery according to any one of Claims 1 to 3, wherein said non-aqueous solvent except the vinyl ethylene carbonate compound of the general formula (I) contains one or more solvents selected from solvents having a relative dielectric constant of not smaller than 25 and exhibits a flash point of not lower than 70°C.

6. The non-aqueous electrolyte secondary battery according to any one of Claims 1 to 3, wherein said non-aqueous solvent except the vinyl ethylene carbonate compound of the general formula (I) is selected from solvents having a relative dielectric constant of not smaller than 25.


7. The non-aqueous electrolyte secondary battery

According to Claim 5 or 6, wherein said solvent having a relative dielectric constant of not smaller than 25 is selected from ethylene carbonate, propylene carbonate, butylene carbonate, γ -butyrolactone and γ -valerolactone.

8. The non-aqueous electrolyte secondary battery according to Claim 5 or 6, wherein said solvent having a relative dielectric constant of not smaller than 25 is a mixture of ethylene carbonate and γ -butyrolactone.


9. The non-aqueous electrolyte secondary battery according to any one of Claims 1 to 8, wherein said lithium salt is at least one salt selected from LiClO_4 , LiPF_6 , LiBF_4 , LiCF_3SO_3 , $\text{LiN}(\text{CF}_3\text{SO}_2)_2$, $\text{LiN}(\text{CF}_3\text{CF}_2\text{SO}_2)_2$, $\text{LiN}(\text{CF}_3\text{SO}_2)(\text{C}_4\text{F}_9\text{SO}_2)$ and $\text{LiC}(\text{CF}_3\text{SO}_2)_3$.

10. A non-aqueous electrolyte for non-aqueous electrolyte secondary battery comprising at least a negative electrode and a positive electrode capable of absorbing/releasing lithium which comprises a solute and a non-aqueous solvent, characterized in that said non-aqueous solvent contains a vinyl ethylene carbonate compound represented by the following general formula (I) in an amount of from 0.01 to 20% by weight:



wherein R^1 , R^2 , R^3 , R^4 , R^5 and R^6 each independently represent a hydrogen atom or an alkyl group having 1 to 4 carbon atoms.

11. A non-aqueous electrolyte for non-aqueous electrolyte secondary battery comprising at least a negative electrode and a positive electrode capable of absorbing/releasing lithium which comprises a solute and a non-aqueous solvent, characterized in that said non-aqueous solvent contains one or more solvents selected from solvents having a relative dielectric constant of not smaller than 25 in an amount of not smaller than 90% by weight, exhibits a flash point of not lower than 70°C and comprises at least one vinylene carbonate represented by the following general formula (I) incorporated therein:



wherein R¹, R², R³, R⁴, R⁵ and R⁶ each independently represent a hydrogen atom or an alkyl group having 1 to 4 carbon atoms.

[illegible]